




Date: Sep.07,2020 Date of Receipt: Aug.24,2020

Report No.: TFF9H635 Quantity: 1PC (P1/1) Ref. No.: NIL
MAGICAL FILM ENTERPRISE CO., LTD Filter Media

Report Title: _____ Item: _____
Address: No. 36, Aly. 378, Sec. 2, Yongxing Rd., Wuqi Dist., Taichung City 435, Taiwan (R.O.C.)

Test Items		Test Results	Test Methods
Sub-Micron Particulate Filtration Efficiency(%) (0.1 μm PSL)	1	98.48	ASTM F2100-2019 9.3
	2	98.51	ASTM F2299-2017
	3	98.48	Flow rate:28.1
	4	98.44	(Liter/min)
	5	98.48	
	Ave.	98.48	

Note: Sample description is given by the client: Meltblown 148504



- Note: 1.This report is only responsible for the submitted sample(s), which will be kept for one month period.
2.This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
3.The test report should not be used for public advertisement and commercial promotion.

Authorized by president of Jw-hung Kao
Taiwan Textile Research Institute

Director,
Department of Testing and Certification
Taiwan Textile Research Institute
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)
Tel : +886-2-22670321 ext. 7107, 7110
Fax : +886-2-22675108 , +886-2-22689839



TEST REPORT TUCHENG

COPY

Date: Sep.07,2020 Date of Receipt: Aug.24,2020


Report No.: TFF9H636 Quantity: IPC (P1/1) Ref. No.: NIL
MAGICAL FILM ENTERPRISE CO., LTD Filter Media

Report Title: _____ Item: _____
No. 36, Aly. 378, Sec. 2, Yongxing Rd., Wuqi Dist., Taichung City 435, Taiwan (R.O.C.)

Address: _____

Test Items		Test Results	Test Methods
Sub-Micron Particulate Filtration Efficiency(%) (0.1 μm PSL)	1	98.29	ASTM F2100-2019 9.3
	2	98.25	ASTM F2299-2017
	3	98.27	Flow rate:28.1
	4	98.27	(Liter/min)
	5	98.28	
	Ave.	98.27	

Note: Sample description is given by the client: Meltblown 148504 100°C 24h



- Note: 1.This report is only responsible for the submitted sample(s), which will be kept for one month period.
2.This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
3.The test report should not be used for public advertisement and commercial promotion.

Authorized by president of Jw-hung Kao
Taiwan Textile Research Institute

Director,
Department of Testing and Certification
Department of Testing and Certification, Taiwan Textile Research Institute
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)
Tel : +886-2-22670321 ext. 7107, 7110
Fax : +886-2-22675108 , +886-2-22689839