財團法人紡織產業綜合研究所 Taiwan Textile Research Institute





Aug.17,2020 Date:	Jul.30,2020 Date of Receipt:	TEST REPORT	TUCHENG	ORIGINAL
TFF9G820	1PC	(P1/1)	NIL	
Report No.:MAGICAL F	Quantity: Pag	re Order/Pages:	_Ref. No.: Filter Media	
Report Title: No. 36, Aly. 3 Address:	78, Sec. 2, Yongxing Rd., Wuq	i Dist., Taichung Ci	<u>Item:</u> ty 435, Taiwan (R.O.C.)	

Test Items Test Results Test Methods ASTM F2100-2019 9.3 Sub-Micron Particulate 98.17 1 98.16 ASTM F2299-2017 Filtration Efficiency(%) 2 97.87 Flow rate:28 $(0.1 \mu \text{m PSL})$ 98.03 (Liter/min)

97.99

Note: Sample description is given by the client: Meltblown NO.KOO2

5

Ave.

Note: The test report is the test results issued by the testing institution as requested by the consignor, it shall not determine the legitimacy of the product.



Note: 1. This report is only responsible for the submitted sample(s), which will be kept for one month period.

- 2. This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- The test report should not be used for public advertisement and commercial promotion.

Authorized by president of Taiwan Textile Research Institute

Jui - hung

Director.

Department of Testing and Department of Testing and Department of Testing and Certification, Convention Research Institute

No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)

Tel: +886-2-22670321 ext. 7107, 7110 Fax: +886-2-22675108, +886-2-22689839